



ROMPOX® - PURE | DEKO

The decorative grit and gravel hardener


No more loose stones landing on the lawn, the patio or even in the house. With ROMPOX® - DEKO, grit and gravel can be bonded together to create a sure-footed, visually appealing surface. Whether light wells around the house, decorative surfaces, tree surrounds or garden paths, with the 1 component resin binder for washed, dried and dust-free grit / gravel all garden projects can be achieved. The light stability makes ROMPOX® - DEKO especially suitable for light stones. The surfaces are water permeable and easy to clean.

Properties

- surface depths from 30 mm | 1 ¼"
- no offensive odour
- frost and de-icing salt resistant
- UV and water resistant
- suitable for light grit/gravel



Colour examples for separately bought grit/gravel



ROMPOX® - PURE | DEKO

The decorative grit and gravel hardener

APPLICATION

Construction site requirements: The foundation needs to be prepared according to the expected traffic loads. Superstructure and substructure must be water permeable. Regulations and leaflets regarding construction of paved stone surfaces should be heeded. Future loads must not cause the surface to settle or loosen stones. Ideally, you would use ROMEX® Trass-Bed products. For optimum application it is recommended using ROMEX® application tools.

Preparation: Prepare surface for hardening by making sure it is compact and stable to a depth of at least 30 mm | 1 ¼". Adjoining surfaces that are not to be joint-fixed are taped off. Not all grit/gravel bought from the construction trade or DIY shop is clean and dry, therefore it is important to carry out cleaning and drying before using ROMPOX® - DEKO.

Here two types of cleaning:

1. Pour gravel or grit into a concrete mixer, add enough clean water and mix well for at least 1 minute. After completing the mixing process carefully pour the cloudy water out of the mixer. Repeat the process until the emptied water is almost clear and the grit/gravel is clean. Spread the washed gravel in a thin layer on a fleece or mat and allow to dry completely (ideally under direct sunlight).

2. Fill a clean mortar trough with clean water, pour the grit/gravel into a metal basket or similar, dip the metal basket into the mortar trough, and move it up and down until the gravel is cleaned. Then let the grit/gravel dry as described above.

Mixing: See mixing ration in the consumption table !

Pour the clean and dry grit/gravel into the pug mill mixer or free fall mixer and start the mixing process. Open the tin within and pour the contents completely into the grit/gravel. In order to fully use the container content, the tin should be scraped out. Total mixing time: at least 6 minutes. Note: Store the tin in a warmer environment before use to facilitate emptying since the contents of the tin will flow more easily. Storage of the tin in a cooler environment makes emptying difficult, since the contents of the tin are then somewhat more viscous. In this case, special care must be taken to ensure that the tin is completely emptied. Basically: the more tin content is used, the better the end result.


Application: Pour the ready to use mix onto the prepared surface; if necessary, disperse it with a shovel and draw off on the same level in a coat height of at least 30 mm | 1 ¼" with a level rod. Using a mason's trowel, work it in well so it is deep and compact. Trowel surface. Good compacting is essential for a durable end product! Take care to avoid impurities by binding agent and footprints on the stone surface.

Subsequent treatment: The freshly jointed surface needs to be protected against rain for the next 12–24 hours. The rain protection layer must not be laid directly onto the paved surface, to ensure sufficient air circulation. Particularly heavy used surfaces (e.g. public tree pits) have to install with a surface depth of min. 5 cm. Immediately after the surface has hardened, ROMPOX® - DEKO is painted over the stone surface undiluted using a paintbrush or fur roller as a sealant. This ensures an even better surface strength. Consumption for subsequent sealing: approx. 200–300 ml/m² | 0.04–0.06 lbs/sqft. This process is repeated on average every 3 years.

Important notes: In case of uncertainty, a sample surface should be tested before the entire jointing is done. Washed grit/gravel must be completely dry. In connection with dampness it can lead to loss of strength!

Technical data

System	1-component PU		
Compressive strength	6.3 N/mm² 914 psi Building site value	DIN 1164 part 7	
Bending tensile strength	1.75 N/mm² 254 psi Building site value	DIN 1164 part 7	
Hard mortar raw density	1.65 kg/dm³ 0.95 oz/in³ Building site value	DIN 1164 part 7	
Application time at 20 °C 68 °F	20–30 minutes	ROMEX®-norm 04	
Application temperature	> 7 °C up to max. 30 °C > 44.6 °F up to max. 86 °F At lower temperatures slow hardening, at high temperatures quick hardening		
Re-opening of surface at 20 °C 68 °F	after 24 hours can be walked on, after 6 days fully load bearing		
Water permeability	very high permeable depending on grain size		
Storage life	12 months, frostfree, dry		




Approx. consumption per 1 m² at Ø 30 mm surface depth:
Pedestrian loads:
1 kg | 2.2 lbs ROMPOX® - DEKO + 50 kg | 110 lbs grit/gravel grainsize of approx. 2–5 to 8–11 mm | ½"–¾" to ¾"

!

Examples: Consumption binding agent grit strengthening per m²*

Material	Density	Minimum depth	Quantity of grit/gravel	Quantity of binder
2–5 mm Granite grit	1 720 kg/m³	3 cm	52 kg	1,0 kg
4–8 mm Grit	1 360 kg/m³	3 cm	41 kg	0,8 kg
8–11 mm Grit	1 420 kg/m³	3 cm	43 kg	0,9 kg
12–16 mm Round gravel	1 580 kg/m³	5 cm	79 kg	1,6 kg
16–22 mm Grit	1 480 kg/m³	7 cm	104 kg	2,1 kg
32–45 mm Round gravel	1 620 kg/m³	15 cm	243 kg	4,9 kg




Approx. consumption per 0,25 m² at Ø 50 mm surface depth:
Light traffic loads up to 3 t:
1 kg | 2.2 lbs ROMPOX® - DEKO + 25 kg | 55 lbs grainsize of approx. 2–5 mm to 4–8 mm | ½"–¾" to ¾"

Only with settlement-free, water permeable bedding and base course. We recommend ROMPOX® - TRASS-BED as bedding mortar. Immediately after hardening of the surface, the ROMPOX® - DEKO binding agent that was used is applied undiluted with a brush or fur roller to the stone surface to act as sealant. This process ensures an even better surface strength. Consumption for subsequent sealing: approx. 200–300 ml/m² | 0.04–0.06 lbs/sqft.

Examples: Consumption binding agent grit strengthening per m²*

Material	Density	Minimum depth	Quantity of grit/gravel	Quantity of binder
2–5 mm Granite grit	1 720 kg/m³	5 cm	86 kg	3,4 kg
4–8 mm Grit	1 360 kg/m³	5 cm	68 kg	2,7 kg



* Please note that the calculation of the weight for the grit/gravel is only an approximation. The materials used are natural building materials and are therefore subject to natural fluctuations. When compacted, the volume decreases, by what the demand/quantity increases. Note on the surface depth: The surface should be three times as deep as the largest grain of the grit/gravel used to obtain a homogeneous and stable surface. Only washed and dry fillers are to be used.

The information printed in this brochure is based on experiential values and the current levels of knowledge in science and practice, however they are not binding and have no legal force. All previous information becomes invalid with the issue of this brochure. Images similar. Effective June 2020. We reserve the right to make changes.

ADVERSE WEATHER WARNING!
CALL ROMEX® BEFORE INSTALL!
604-612-3649

Follow us:




ROMEX® NORTH AMERICA
 toll-free: 1-844-529-2330
 info@romex.us
 www.romex.us
 info@romexcanada.com
 www.romexcanada.com

